



ISOPON P38 LITE

Super Lightweight Body Filler

Description	<p>ISOPON P38 Lightweight polyester body filler is a two component paste used for the filling of holes and imperfections in most substrates.</p> <p>ISOPON P38 Lightweight has been specially formulated for the professional using the latest technology in lightweight body fillers, and it combines excellent filling properties together with the easiest sanding of all the David's ISOPON fillers.</p>
Surface preparation & instructions for use	<p>ISOPON P38 Lightweight polyester filler can be used on the following surfaces:-</p> <ul style="list-style-type: none">• Bare metal – e.g. Steel, degrease and abrade with P80 paper.• Original paint surfaces (with the exception of thermoplastic acrylics) degrease and abrade with P180 grit paper.• GRP degrease and abrade with P80 grit paper.
Health and Safety Statement	<p><u>FOR PROFESSIONAL USE ONLY</u>. Read full instructions before use.</p> <p>IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at WWW.U-POL.COM.</p> <p>U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.</p>
Mixing Ratio	<p>100 parts by weight ISOPON P38 polyester filler, 2 parts by weight ISOPON hardener for polyester filler.</p> <p>The exact mixing ratio is not critical, although over or under catalyzation may affect the gel time. Do not greatly over catalyze the paste as this will not significantly speed up the gel time and could lead to bleed through and bleaching problems when over-painting later. Staining may also occur where too little hardener is used.</p>
Pot life	Once mixed, 4-5 mins. at 20°C with 2% hardener.
Tools	Mixing board, filler knife, plastic or rubber spatula
Drying Time	Sandable after 15 mins. at 20°C. IMPORTANT – This fillers is very easy to sand and therefore recommend that nothing coarser or lower than P80 paper is used.
Over painting	ISOPON P38 Lightweight polyester filler can be over-painted with most paint systems including 2K.
Product Codes	P38/5 – 3 Litre Paste Kit
VOC Information	The EU limit for this product (product category: IIBb) in ready to use form is 250g/litre. The VOC content of this product in ready to use form is 100g/litre

U-POL, 1 TOTTERIDGE LANE, WHETSTONE, LONDON, N20 0EY, UK
Home Sales T: +44(0)870 899 8200; F:+44(0)870 899 8211; E: sales@u-pol.com
Export Sales T: +44(0)870 899 8200; F:+44(0)870 899 8299; E: exportsales@u-pol.com
Technical T: +44(0)870 899 8310; F:+44(0)870 899 8351; E: technicaldepartment@u-pol.com
WEBSITE: WWW.U-POL.COM